



新榮科技公司 SUN WING TECHNOLOGY COMPANY

香港九龍長沙灣長順街 20 號時豐中心 9 樓, 908 室
Workshop 8, 9/F, Premier Centre, 20, Cheung Shun Street, Lai Chi Kok, Kowloon, Hong Kong
Tel: (852) 2396 2884, (852) 2332 8806 Fax: (852) 2787 4865
E-mail: sunwingt@netvigator.com Web Site: <http://www.sunwingtechnology.com>



刷鍍銠電鍍液

Use: Brush and spot plating

Reynolds Rhodium Pen Plating Solution is a brush plating electrolyte. It yields brilliant bright Rh deposits. The white Rhodium layer can reach 0.1 micron. The solution is ready-to-use.

Specification

Rh-content	= 2.0 g Rh/100ml
Colour	red solution
Bath voltage	= 10 volts
pH	< 1
Temperature (°C)	Room Temperature

威諾士刷鍍銠電鍍液能產生光亮雪白的銠鍍層。適用於小部位及難鍍之處，鍍層厚度能達 0.1 微米，鍍液可以直接刷鍍。

電鍍條件

銠含量	= 2.0 g Rh/100ml
顏色	紅色
電壓	= 10 volts
pH	< 1
溫度 (°C)	室溫