



新榮科技公司

SUN WING TECHNOLOGY COMPANY

九龍塘尾道 54-58 號永利工業大廈二樓 205 室  
Room 205, 2/F, Wing Lee Ind. Bldg, 54-58, Tong Mei Rd., Kln, HK  
Tel: 2396 2884, 2332 8806 Fax: 2787 4865

E-mail: [sunwingt@netvigator.com](mailto:sunwingt@netvigator.com) Web Site: <http://www.sunwingtechnology.com>

## PLATING RESIST BLACK

**Properties:** extremely high chemical resistance  
easy to operate .  
good adhesion on steel and brass  
high elasticity  
One-coat-finish  
easy to remove



### **Processing:**

For spraying, it has to be diluted with White Spirit or Fast Drying Thinner in a ratio of 1:0.5 to 1:0.3. For brushing, just add a little Fast Drying Thinner. Coating layer should be uniform but not too thick.

For spraying we recommend a spray gun with a 1.5mm spray nozzle and 2.5 to 3atmospheric pressure.

**Air Drying time:** About 2 hours

**Stoving time:** 80 °C for 10 min.

**Removing method:** Trichlorethylene

### **Application:**

Specially designed as a stop-off lacquer for watch bracelets.

## 電鍍絕緣油

**性質：**  
抗化學性極佳  
容易操作  
對鍍及鍍的附着力優良  
彈性高  
一組份塗層  
易於剝除

### **使用法：**

噴塗時，絕緣油：白火酒<sup>1</sup>或快乾天那水=1:0.5至1:0.3，筆塗則加少許快乾天那水稀釋絕緣油

建議噴槍口徑為 1.5mm，其壓力為 2.5至3個大氣壓力。噴塗均勻即可，不宜過厚。

**乾燥時間：**室溫下乾約兩小時

**焗乾時間：**在80°C溫度下焗10分鐘

**剝離法：**以三氯乙烯清洗

**用途：**特別適合於表殼及表帶的選擇性電鍍

<sup>1</sup> 白火酒化學名稱為丙醇