



新榮科技公司

SUN WING TECHNOLOGY COMPANY

九龍塘尾道 54-58 號永利工業大廈二樓 205 室
Room 205, 2/F, Wing Lee Ind. Bldg, 54-58, Tong Mei Rd., Kln, HK
Tel: 2396 2884, 2332 8806 Fax: 2787 4865

E-mail: sunwingt@netvigator.com Web Site: <http://www.sunwingtechnology.com>

PLATING RESIST BLACK

Properties: extremely high chemical resistance
easy to operate .
good adhesion on steel and brass
high elasticity
One-coat-finish
easy to remove



Processing:

For spraying, it has to be diluted with White Spirit or Fast Drying Thinner in a ratio of 1:0.5 to 1:0.3. For brushing, just add a little Fast Drying Thinner. Coating layer should be uniform but not too thick.

For spraying we recommend a spray gun with a 1.5mm spray nozzle and 2.5 to 3atmospheric pressure.

Air Drying time: About 2 hours

Stoving time: 80 °C for 10 min.

Removing method: Trichlorethylene

Application:

Specially designed as a stop-off lacquer for watch bracelets.

電鍍絕緣油

性質：
抗化學性極佳
容易操作
對鍍及鍍的附着力優良
彈性高
一組份塗層
易於剝除

使用法：

噴塗時，絕緣油：白火酒¹或快乾天那水=1:0.5至1:0.3，筆塗則加少許快乾天那水稀釋絕緣油

建議噴槍口徑為 1.5mm，其壓力為 2.5至3個大氣壓力。噴塗均勻即可，不宜過厚。

乾燥時間：室溫下乾約兩小時

焗乾時間：在80°C溫度下焗10分鐘

剝離法：以三氯乙烯清洗

用途：特別適合於表殼及表帶的選擇性電鍍

¹ 白火酒化學名稱為丙醇